

Enamelled copper wire **CUL 500/0,85**



Picture shows CUL 100/0,22

Advantages

Insulating varnish basis min. polyurethane, mod.

Grade 1, TJ min. 155 °C

Solderable

Applications

Enamelled copper wire for the production of coils and windings and for general laboratory needs. Please consider the relevant standards.

Approvals



Enamelled copper wire **CUL 500/0,85**

Type

CUL 500/0,85

Type

CUL 500/0,85



Electrical data



Mechanical data

Operating data

Current rating 2.00 A

Environment

Heat resistance 155 °C (CLF)

Insulating varnish min. Polyurethan, mod.

Tin-plate >350 °C

Measures and weights

Length m (min.) 77

Wire diameter 0.85 mm

Weight 0.50 kg

Subject to change.